

## (12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property  
Organization  
International Bureau



(43) International Publication Date  
18 March 2004 (18.03.2004)

PCT

(10) International Publication Number  
**WO 2004/022853 A1**

(51) International Patent Classification<sup>7</sup>: **E01C 13/06**,  
13/08, C09K 17/18, 17/40, C08K 9/08, C09C 3/10, 1/30,  
3/00

(21) International Application Number:  
PCT/DK2003/000573

(22) International Filing Date:  
2 September 2003 (02.09.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
02078648.9 6 September 2002 (06.09.2002) EP

(71) Applicant (*for all designated States except US*):  
PV-SAND A/S [DK/DK]; Ågade 103, Pjedsted,  
DK-7000\_Fredericia (DK).

(72) Inventor; and

(75) Inventor/Applicant (*for US only*): JENSEN, Victor  
[DK/DK]; Herningsholmvej 14, DK- 7400\_Herning (DK).

(74) Agent: PATENTGRUPPEN ApS; Arosgården, Åboule-  
varden 31, DK-8000 Aarhus C (DK).

(81) Designated States (*national*): AE, AG, AL, AM, AT (util-  
ity model), AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA,  
CH, CN, CO, CR, CU, CZ (utility model), CZ, DE (util-  
ity model), DE, DK (utility model), DK, DM, DZ, EC, EE  
(utility model), EE, ES, FI (utility model), FI, GB, GD, GE,  
GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ,  
LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN,  
MW, MX, MZ, NI, NO, NZ, OM, PG, PH, PL, PT, RO,  
RU, SC, SD, SE, SG, SK (utility model), SK, SL, SY, TJ,  
TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA,  
ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,  
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),  
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),  
European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,  
ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO,  
SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM,  
GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

**Published:**

— with international search report

*For two-letter codes and other abbreviations, refer to the "Guid-  
ance Notes on Codes and Abbreviations" appearing at the begin-  
ning of each regular issue of the PCT Gazette.*

(54) Title: COATED SAND GRAINS

(57) Abstract: A particulate material is disclosed consisting of sands grains coated with a thermoplastic polymer having a melt index of 20-40g/10 min and Shore A hardness of 40-90, to provide a loose material with properties suitable for use as a surfacing composition, in particular for sports surfaces such as fields of artificial grass. Preferably a coupling agent is provided between the grains and the polymer. A method of producing such particulate material is furthermore disclosed, in which the sand is heated to a temperature within the range of 200° to 300°C and mixed with a portion of a thermoplastic polymer, where after an amount of water is added to the mixture under continued operation of the mixer, and an airflow finally is directed through the content of the mixer so as to lower the temperature thereof.